

## Metric thread stud bolts

**DIN**  
976-1

ICS 21.060.10

Supersedes September 1986 edition of DIN 976.

Descriptors: Fasteners, stud bolts.

Gewindebolzen. Teil 1: Metrisches Gewinde

*In keeping with current practice in standards published by the International Organization for Standardization (ISO), a comma has been used throughout as the decimal marker.*

Dimensions in mm

## 1 Scope and field of application

This standard specifies dimensions and technical delivery conditions for stud bolts with metric thread designed to perform functions similar to those of double end studs (clamping type or interference-fit type).

This standard covers stud bolts with threads produced to tolerance 6g which is customary for bolt/nut assemblies of thread engagement group N as specified in DIN 13-14. Attention is drawn to the fact that stud bolts with lengths exceeding those specified for thread engagement group N might not be true to gauge.

For stud bolts with thread of size greater than M39, the specifications of this standard apply only with regard to dimensions and tolerances, the other properties being subject to agreement between purchaser and manufacturer.

Stud bolts may be supplied either with ends cut square (type A) or with chamfered ends (type B), as specified in DIN 78.


## 2 Dimensions

### Type A DIN 78—Ko type ends



### Type B DIN 78—K type ends

(only for nominal lengths,  $l$ , of 500 mm or less)



Continued on pages 2 to 6.

Table 1: Dimensions

Thread size			M2	M2,5	M3	(M3,5)	M4	M5	M6	M8	M10	M12	
			—	—	—	—	—	—	—	—	M8 × 1	M10 × 1,25	M12 × 1,25
			—	—	—	—	—	—	—	—	—	M10 × 1	M12 × 1,5
Nominal size	<i>l</i>		Approximate mass (7,85 kg/dm <sup>3</sup> ) per 1 000 units, in kg										
	min	max											
5	4,76	5,24	0,09	0,15									
6	5,76	6,24	0,11	0,18									
8	7,71	8,29	0,15	0,24	0,27								
					0,35	0,48	0,62						
10	9,71	10,29	0,19	0,30	0,44	0,60	0,78	1,24					
12	11,65	12,35	0,22	0,36	0,53	0,72	0,93	1,49	2,12				
(14)	13,65	14,35	0,26	0,42	0,62	0,84	1,09	1,73	2,47				
16	15,65	16,35	0,30	0,48	0,71	0,95	1,24	1,98	2,82	5,10			
(18)	17,65	18,35	0,34	0,54	0,79	1,07	1,40	2,23	3,18	5,73			
20	19,58	20,42	0,37	0,60	0,88	1,19	1,55	2,48	3,53	6,37	10,0		
(22)	21,58	22,42	0,41	0,66	0,97	1,31	1,71	2,72	3,88	7,01	11,0		
25	24,58	25,42	0,47	0,75	1,10	1,49	1,94	3,09	4,41	7,96	12,6	18,2	
(28)	27,58	28,42	0,52	0,84	1,24	1,67	2,17	3,47	4,94	8,92	14,1	20,3	
30	29,58	30,42	0,56	0,90	1,32	1,79	2,32	3,71	5,29	9,56	15,1	21,8	
35	34,5	35,5	0,66	1,05	1,53	2,09	2,71	4,33	6,18	11,1	17,5	25,5	
40	39,5	40,5	0,75	1,20	1,74	2,39	3,10	4,95	7,06	12,7	20,1	29,1	
45	44,5	45,5		1,35	1,94	2,69	3,49	5,57	7,94	14,3	22,5	32,7	
50	49,5	50,5		1,50	2,15	2,99	3,88	6,19	8,82	15,9	25,1	36,4	
55	54,4	55,6			2,36	3,29	4,27	6,81	9,71	17,5	27,5	40,0	
60	59,4	60,6			2,58	3,59	4,66	7,43	10,6	19,1	30,1	43,7	
65	64,4	65,6				3,89	5,05	8,05	11,5	20,7	32,5	47,3	
70	69,4	70,6				4,20	5,44	8,67	12,4	22,3	35,2	50,9	
75	74,4	75,6					5,83	9,29	13,3	23,9	37,7	54,7	
80	79,4	80,6					6,22	9,91	14,2	25,5	40,2	58,2	
(85)	84,3	85,7						10,5	15,1	27,1	42,7	61,8	
90	89,3	90,7						11,2	15,9	28,7	45,2	65,5	
(95)	94,3	95,7						11,8	16,8	30,3	47,7	69,1	
100	99,3	100,7						12,4	17,7	31,9	50,2	72,8	
110	109,3	110,7							19,5	35,1	55,2	80,0	
120	119,3	120,7							21,3	38,3	60,2	87,3	
130	129,2	130,8								41,5	65,1	94,6	
140	139,2	140,8								44,7	70,1	102	
150	149,2	150,8								47,9	75,1	109	
160	159,2	160,8								51,1	80,1	117	
170	169,2	170,8									85,0	124	
180	179,2	180,8									90,0	131	
190	189,075	190,925									95,0	138	
200	199,075	200,925									99,9	146	
220	219,075	220,925										160	
240	239,075	240,925										175	
1 000	995,5	1 004,5	19,0	30,0	43,0	59,8	77,6	124	177	319	502	728	
2 000	1 992,5	2 007,5	38,0	60,0	86,0	120	155	248	354	638	1 004	1 456	
3 000	2 989,5	3 010,5	57,0	90,0	129	179	233	372	531	957	1 506	2 184	

(continued)

Table 1 (continued)

Thread size			(M 14)	M 16	(M 18)	M 20	(M 22)	M 24	(M 27)	M 30	(M 33)	M 36
			(M14 × 1,5)	M16 × 1,5	(M18 × 1,5)	M20 × 1,5	(M22 × 1,5)	M24 × 2	(M27 × 2)	M30 × 2	(M33 × 2)	M36 × 3
Nominal size	l		Approximate mass (7,85 kg/dm <sup>3</sup> ) per 1 000 units, in kg									
	min.	max.										
30	29,58	30,42	29,8	40,0								
35	34,5	35,5	34,8	46,6	57,9							
40	39,5	40,5	39,8	53,3	66,1	83,3						
45	44,5	45,5	44,8	60,0	74,4	93,7	115					
50	49,5	50,5	49,7	66,6	82,7	104	128	150				
55	54,4	55,6	54,7	73,3	90,9	115	141	165	213			
60	59,4	60,6	59,7	80,0	99,2	125	154	180	232	284		
65	64,4	65,6	64,6	86,6	107	135	166	195	251	308	378	
70	69,4	70,6	69,6	93,3	116	146	179	210	271	332	407	482
75	74,4	75,6	74,6	100	124	156	192	225	290	355	437	516
80	79,4	80,6	79,6	107	132	167	205	240	310	379	466	550
(85)	84,3	85,7	84,5	113	141	177	218	255	329	403	495	585
90	89,3	90,7	89,5	120	149	187	230	270	348	427	524	619
(95)	94,3	95,7	94,5	127	157	198	243	285	368	450	553	653
100	99,3	100,7	99,5	133	165	208	256	300	387	474	582	688
110	109,3	110,7	109	147	182	229	282	330	426	521	640	757
120	119,3	120,7	119	160	198	250	307	360	464	569	698	825
130	129,2	130,8	129	173	215	271	333	390	503	616	757	894
140	139,2	140,8	139	187	231	291	358	420	542	664	815	963
150	149,2	150,8	149	200	248	312	383	450	580	711	873	1032
160	159,2	160,8	159	213	265	333	410	480	619	758	931	1101
170	169,2	170,8	169	226	281	354	435	510	658	806	990	1169
180	179,2	180,8	180	239	298	375	461	540	696	853	1048	1238
190	189,075	190,925	190	252	315	396	486	570	735	901	1106	1307
200	199,075	200,925	199	265	332	416	512	600	774	948	1164	1376
220	219,075	220,925	218	291	366	456	563	660	851	1043	1281	1513
240	239,075	240,925	237	317	400	496	614	720	929	1138	1397	1651
260	258,95	261,05	256	343	434	535	665	780	1006	1232	1513	1788
280	278,95	281,05	275	369	468	575	716	840	1083	1327	1630	1926
300	298,95	301,05		395	502	615	767	900	1161	1422	1746	2064
320	318,85	321,15		421	536	655	818	960	1239	1517	1862	2202
340	338,85	341,15			570	694	869	1020	1317	1612	1978	2340
360	358,85	361,15			604	734	920	1080	1395	1707	2094	2478
380	378,85	381,15				774	971	1140	1473	1802	2210	2616
400	388,85	401,15				815	1022	1200	1551	1897	2326	2754
420	418,75	421,25					1073	1260	1629	1992	2442	2892
440	438,75	441,25						1124	1320	1707	2087	2548
460	458,75	461,25							1380	1785	2182	2674
480	478,75	481,25							1440	1863	2277	2790
500	498,75	501,25								1941	2372	2906
1000	995,5	1004,5	995	1330	1650	2080	2560	3000	3882	4744	5812	6888
2000	1992,5	2007,5	1990	2660	3300	4160	5120	6000	7764	9488	11624	13776
3000	2989,5	3010,5	2985	3990	4950	6240	7680	9000	11646	14232	17436	20664

(continued)

Table 1 (concluded)

Thread size			(M39)	M42	(M45)	M48	(M52)	M56	(M60)	M64	(M68)	—
			(M39×3)	M42×3	(M45×3)	M48×3	(M52×3)	M56×4	(M60×4)	M64×4	(M68×4)	M72×6
Nominal size	l		Approximate mass (7,85 kg/dm <sup>3</sup> ) per 1 000 units, in kg									
	min.	max.										
80	79,4	80,6	654									
(85)	84,3	85,7	694									
90	89,3	90,7	735	847								
(95)	94,3	95,7	776	894								
100	99,3	100,7	817	941	1091	1235						
110	109,3	110,7	899	1036	1201	1358						
120	119,3	120,7	980	1131	1310	1482	1758	2034				
130	129,2	130,8	1062	1224	1419	1605	1905	2203	2552	2895		
140	139,2	140,8	1143	1318	1528	1729	2052	2372	2748	3118	3547	
150	149,2	150,8	1225	1412	1637	1852	2198	2542	2945	3341	3800	4289
160	159,2	160,8	1307	1506	1747	1976	2345	2711	3141	3563	4054	4575
170	169,2	170,8	1389	1600	1856	2099	2491	2881	3337	3786	4307	4861
180	179,2	180,8	1471	1695	1965	2223	2637	3050	3533	4009	4560	5147
190	189,075	190,925	1552	1789	2074	2346	2784	3219	3729	4232	4814	5433
200	199,075	200,925	1634	1883	2183	2470	2931	3389	3926	4455	5067	5719
220	219,075	220,925	1797	2071	2401	2716	3224	3728	4319	4901	5574	6291
240	239,075	240,925	1961	2260	2620	2963	3517	4067	4712	5347	6080	6863
260	258,95	261,05	2124	2448	2838	3210	3810	4406	5104	5793	6587	7435
280	278,95	281,05	2288	2636	3056	3457	4103	4745	5497	6239	7094	8007
300	298,95	301,05	2451	2824	3275	3704	4396	5084	5889	6682	7600	8579
320	318,85	321,15	2614	3013	3493	3951	4689	5423	6282	7127	8107	9150
340	338,85	341,15	2778	3201	3711	4198	4982	5762	6675	7572	8614	9722
360	358,85	361,15	2941	3389	3930	4445	5275	6101	7067	8017	9121	10294
380	378,85	381,15	3104	3578	4148	4692	5568	6440	7460	8462	9627	10866
400	388,85	401,15	3267	3766	4366	4939	5861	6779	7853	8908	10134	11438
420	418,75	421,25	3430	3954	4585	5186	6155	7118	8245	9354	10641	12009
440	438,75	441,25	3593	4142	4803	5433	6448	7457	8638	9799	11147	12582
460	458,75	461,25	3756	4330	5021	5680	6741	7796	9030	10245	11654	13154
480	478,75	481,25	3919	4518	5239	5927	7034	8134	9423	10690	12161	13726
500	498,75	501,25	4082	4706	5457	6174	7327	8473	9816	11136	12667	14298
1000	995,5	1004,5	8164	9412	10914	12348	14654	16946	19632	22272	25334	28596
2000	1992,5	2007,5	16328	18824	21828	24696	29308	33892	39264	44544	50668	57192
3000	2989,5	3010,5	24492	28236	32742	37044	43962	50838	58796	66816	76002	85788

Stud bolts are generally manufactured in the sizes for which a value of mass has been specified.  
 Lengths between 500 mm and 1000 mm shall be graded in 20 mm steps.  
 Bracketed sizes should be avoided if possible.

### 3 Technical delivery conditions

Table 2

Material		Steel	Stainless steel	Nonferrous metal
General requirements		As specified in ISO 8992.		
Thread	Tolerance	6g		
	As specified in	DIN 13-15.		
Mechanical properties	Property class (material)	For sizes up to M39: 4.8, 5.8, 8.8 or 10.9 For sizes above M39: subject to agreement.	For sizes up to M39: A2-50 or A4-50 For sizes above M39: subject to agreement.	CuZn <sup>1)</sup> Al <sup>2)</sup>
	As specified in	DIN EN 20 898-1. (test programme B)	ISO 3506	DIN EN 28 839
Limit deviations and geometrical tolerances	Product grade	A		
	As specified in	ISO 4759-1.		
Surface finish		As processed.	Bright.	Bright.
		DIN 267-2 shall apply with regard to surface roughness. DIN EN 26 157-1 shall apply with regard to limits for surface discontinuities for property class 5.8 or less and DIN EN 26 157-3 for property class 8.8 or higher. ISO 4042 shall apply with regard to electroplating. DIN 267-10 shall apply with regard to hot-dip galvanizing.		
Acceptance inspection		As specified in ISO 3269.		
<sup>1)</sup> Copper-zinc alloy CU2 or CU3 (as in DIN EN 28 839), at the manufacturer's discretion. <sup>2)</sup> Aluminium alloy AL1 or AL2 (as in DIN EN 28 839), at the manufacturer's discretion. <sup>3)</sup> For type A stud bolts and nominal lengths exceeding 1 000 mm, the tolerance on length shall be js17 (product grade B as in ISO 4759-1).				

### 4 Designation

Designation of a type A M10 stud bolt with a nominal length,  $l$ , of 80 mm, and assigned to property class 8.8:

Stud bolt DIN 976-1 — M10 × 80 — A — 8.8

Designation of an M10 stud bolt with a nominal length,  $l$ , of 1000 mm, and assigned to property class 8.8:

Stud bolt DIN 976 — M10 × 1 000 — 8.8

The DIN 4000—2—3 tabular layout of article characteristics shall apply to studs as covered in this standard.

## 5 Marking

One end of steel stud bolts of size M5 or greater shall be marked with the symbol for the property class and of stainless steel stud bolts of size M5 or greater, with the symbol denoting the material grade (A2 or A4), omitting the symbol for property class 50.

Marking of nonferrous metal stud bolts is not required.

### Standards referred to

DIN 13-14	ISO metric screw threads; tolerance system for threads 1 mm in diameter and larger
DIN 13-15	ISO metric screw threads; fundamental deviations and tolerances for screw threads of 1 mm diameter and larger
DIN 78	Stud ends and lengths of projection of bolt ends for ISO metric screw threads in accordance with DIN 13
DIN 267-2	Fasteners; technical delivery conditions; design and dimensional accuracy
DIN 267-10	Fasteners; technical delivery conditions; hot-dip galvanized components
DIN 4000-2	Tabular layouts of article characteristics for bolts, screws and nuts
DIN EN 20 898-1	Mechanical properties of fasteners; bolts, screws and studs (ISO 898-1 : 1988)
DIN EN 26 157-1	Fasteners; surface discontinuities. Part 1: Bolts, screws and studs for general requirements
DIN EN 26 157-3	Fasteners; surface discontinuities; bolts, screws and studs for special requirements (ISO 6157-3 : 1988)
DIN EN 28 839	Mechanical properties of fasteners; bolts, screws, studs and nuts made of nonferrous metals
ISO 3269 : 1988	Fasteners; acceptance inspection
ISO 3506 : 1979	Corrosion-resistant stainless steel fasteners; specifications
ISO 4042 : 1989	Threaded components; electroplated coatings
ISO 4759-1 : 1978	Tolerances for fasteners; bolts, screws and nuts with thread diameters from 1,6 to 150 mm; product grades A, B and C
ISO 8992 : 1986	Fasteners; general requirements for bolts, screws, studs and nuts

### Other relevant standard

DIN 976-2	Metric interference-fit thread stud bolts
-----------	---

### Previous editions

DIN 976 : 1970-01, 1986-09.

### Amendments

The following amendments have been made to the September 1986 edition of DIN 976.

- a) The range of commercial sizes for stud bolts of thread size smaller than M45 has been amended.
- b) For type A stud bolts, the range of nominal lengths, *l*, has been extended to include 1000 mm, 2000 mm and 3000 mm.
- c) For stainless steel stud bolts, property class 50 and for steel stud bolts, property classes 4.8, 8.8 and 10.9 have been specified.
- d) The marking of steel and stainless steel stud bolts has been made mandatory.
- e) The standard has been editorially revised.

## Metric interference-fit thread stud bolts

**DIN**  
976-2

ICS 21.060.10

Descriptors: Fasteners, stud bolts.

Gewindebolzen. Teil 2: Metrisches Festsitzgewinde MFS

*In keeping with current practice in standards published by the International Organization for Standardization (ISO), a comma has been used throughout as the decimal marker.*

Dimensions in mm


**1 Scope and field of application**

This standard specifies dimensions and technical delivery conditions for stud bolts intended for use in light metals, including aluminium.

Attention is drawn to the possibility of stud bolts with lengths exceeding those specified for the lengths of engagement in DIN 8141-1 not being true to gauge.

**2 Dimensions**

Stud bolts shall be provided with DIN 78—K type ends.



$u$  (incomplete thread):  $1,5 P$  maximum.

Continued on pages 2 to 4.

Table 1: Dimensions

Thread size			MFS 5	MFS 6	(MFS 7)	MFS 8	MFS 10	MFS 12	(MFS 14)	MFS 16
			—	—	—	MFS 8 × 1	MFS 10 × 1,25	MFS 12 × 1,5	(MFS 14 × 1,5)	MFS 16 × 1,5
Nominal size	<i>l</i>		Approximate mass (7,85 kg/dm <sup>3</sup> ) per 1000 units, in kg							
	min.	max.								
<b>12</b>	11,65	12,35								
<b>(14)</b>	13,65	14,35								
<b>16</b>	15,65	16,35								
<b>(18)</b>	17,65	18,35								
<b>20</b>	19,58	20,42								
<b>(22)</b>	21,58	22,42								
<b>25</b>	24,58	25,42	3,09	4,41						
<b>(28)</b>	27,58	28,42	3,47	4,94						
<b>30</b>	29,58	30,42	3,71	5,29	7,46					
<b>35</b>	34,5	35,5	4,33	6,18	8,70	11,1				
<b>40</b>	39,5	40,5	4,95	7,06	9,94	12,7	20,1			
<b>45</b>	44,5	45,5	5,57	7,94	11,2	14,3	22,6			
<b>50</b>	49,5	50,5	6,19	8,82	12,4	15,9	25,1	36,4		
<b>55</b>	54,4	55,6		9,71	13,7	17,5	27,6	40,0		
<b>60</b>	59,4	60,6		10,6	14,9	19,1	30,1	43,7	59,7	
<b>65</b>	64,4	65,6			16,2	20,7	32,6	47,3	64,6	86,6
<b>70</b>	69,4	70,6			17,4	22,3	35,2	50,9	69,6	93,3
<b>75</b>	74,4	75,6				23,9	37,7	54,6	74,6	99,9
<b>80</b>	79,4	80,6				25,5	40,2	58,2	79,6	107
<b>(85)</b>	84,3	85,7					42,7	61,8	84,5	113
<b>90</b>	89,3	90,7					45,2	65,5	89,5	120
<b>(95)</b>	94,3	95,7					47,7	69,1	94,5	127
<b>100</b>	99,3	100,7					50,2	72,8	99,5	133
<b>110</b>	109,3	110,7						80,0	109	147
<b>120</b>	119,3	120,7						87,3	119	160
<b>130</b>	129,2	130,8							129	173
<b>140</b>	139,2	140,8							139	186
<b>150</b>	149,2	150,8								200
<b>160</b>	159,2	160,8								213

Lengths above 160 mm shall be graded in 10 mm steps.

Bracketed sizes should be avoided if possible.

The zone between the continuous thick lines indicates the range of commercial sizes of stud bolts with interference-fit thread.

Below the dashed line those sizes of stud bolts of property class 10.9 are given which have the minimum length required to ensure a length of engagement equal to 2,5 *d*.



### 3 Technical delivery conditions

Table 2

Material		Steel
General requirements		As specified in ISO 8992.
Thread	Type	Interference-fit thread (MFS)
	As specified in	DIN 8141-1.
Mechanical properties	Property class <sup>1)</sup> (material)	5.6, 8.8 or 10.9
	As specified in	DIN EN 20 898-1.
Limit deviations, geometrical tolerances	Product grade	A
	As specified in	ISO 4759-1.
Surface finish		As processed. DIN 267-2 shall apply with regard to surface roughness. DIN EN 26 157-3 shall apply with regard to limits for surface discontinuities. ISO 4042 shall apply with regard to electroplating (cf. DIN 8141-1).
Acceptance inspection		As specified in ISO 3269.
<sup>1)</sup> Other property classes or materials shall be subject to agreement.		

### 4 Designation

Designation of a stud bolt with a series MFS 12 interference-fit thread, with a nominal length,  $l$ , of 80 mm, and assigned to property class 8.8:

Stud bolt DIN 976-2—MFS 12 × 80—8.8

The DIN 4000—2—3 tabular layout of article characteristics shall apply to studs as covered in this standard.

### 5 Marking

One of the ends of steel stud bolts shall be marked with the property class as specified in DIN EN 20 898-1.

### 6 Use

In order to achieve a tight fit, the studs specified in this standard shall be installed in holes produced to DIN 8141-1.

Nuts provided with a DIN 13-13 metric thread may also be used, without this requiring an increased assembly torque or resulting in loosening or breakage of the assembly.

The length of thread engagement for property classes 5.6 and 8.8 stud bolts shall be approximately equal to  $2d$ , that for property class 10.9, equal to  $2,5d$ .

### Standards referred to

DIN 13-13	ISO metric screw threads; series of preferred sizes for bolts, screws and nuts from 1 mm to 52 mm diameter and limits of size
DIN 78	Thread ends and lengths of projection of bolt ends for ISO metric screw threads in accordance with DIN 13
DIN 267-2	Fasteners; technical delivery conditions; design and dimensional accuracy
DIN 4000-2	Tabular layouts of article characteristics for bolts, screws and nuts
DIN 8141-1	ISO metric coarse and fine pitch screw threads for interference fits in aluminium cast alloys with diameters from 5 to 16 mm; nominal sizes, tolerances and limits of size
DIN EN 20 898-1	Mechanical properties of fasteners; bolts, screws and studs (ISO 898-1 : 1988)
DIN EN 26 157-3	Fasteners; surface discontinuities; bolts, screws and studs for special requirements (ISO 6157-3 : 1988)
ISO 3269 : 1988	Fasteners; acceptance inspection
ISO 4042 : 1989	Threaded components; electroplated coatings
ISO 4759-1 : 1978	Tolerances for fasteners; bolts, screws and nuts with thread diameters from 1,6 to 150 mm; product grades A, B and C
ISO 8992 : 1986	Fasteners; general requirements for bolts, screws, studs and nuts

### Other relevant standard

DIN 976-1	Metric thread stud bolts
-----------	--------------------------

### Explanatory notes

Where small studs with interference-fit thread are to be employed, it is recommended that, for economic reasons, stud bolts with an interference-fit thread be used. However, care should be taken that the required depth of thread engagement is ensured, since stud bolts are not provided with a thread run-out, which normally determines the depth of thread engagement.